

TECHNICAL DATA SHEET

Name of semi-product:

MANIFICA-2D 2020

IUT de bordeaux
I2M département MPI
15 rue Naudet 33175 Gradignan
FRANCE

alexandre.faure.1@u-bordeaux.fr



MANIFICA
CARBON FIBRE RECYCLING PROCESS

MANIFICA-2D 2020 is a range of bidirectional fabrics made of recycled carbon fibres.

High strength & standard modulus aeronautic carbon fibres.



Semi-product description

Typical Product Properties	Unit	Values
Areal weight (ply thickness)	g/m ²	1400 (3 mm)
Areal weight Tolerance	%	± 15
Length x width format	mm ²	300 x 300
Binder content	w%	1-2
Binder type		Polyamide or Epoxy (to be specified)
Binder granulometry	µm	50

Typical Fibres properties

	Unit	
Fibre type		Standard & Intermediate modulus
Fibre diameter	µm	7 ± 2
Fibre length	mm	50-250
Fibres Alignment	%	80 % of fibres aligned within ± 10°

Typical Composite properties:

Compression moulding with cold curing epoxy system

12 bar, 40°C during 3 hours – 24 hours at ambient temperature – 100°C during 4 hours

Typical composite Properties	Unit	Values (range)		Standards
		Min	Max	
Tensile modulus	GPa	40	55	EN 2561
Tensile Strength	MPa	250	300	EN 2561
Interlaminar Shear Strength	MPa	45	60	EN 2563
Fibre volume fraction	%	48	55	
Density	g/cm ³	1.5	1.55	

Health and Safety: Dust and short fibres may cause skin and eye irritation. It is strongly advised to wear, gloves, mask, protective goggles and clothing. Carbon fibres are electrically conductive and may damage unprotected electric installations